

## DISSCO® CSS1h TACK COAT

### CSS1h EMULSIFIED ASPHALT

#### DESCRIPTION

DISSCO CSS1h Tack Coat is a cationic slow setting emulsified asphalt designed to provide adhesion for asphalt patches to existing asphalt pavement, brick or concrete. DISSCO Tack Coat waterproofs the edges of the patch to prevent water intrusion through the joint, and helps prevent pushing and shoving of the patching material by rolling. DISSCO Tack Coat is environmentally friendly containing no solvents.

#### SURFACE PREPARATION

Surface to be tacked should be clean and dry. Remove dirt and debris by hand or mechanical sweeping or with a high-volume blower to remove dirt, loose rock and vegetation.

#### APPLICATION

DISSCO CSS1h Tack Coat is supplied in a concentrate form and may be used directly from the container. Applicator may choose to thin with water prior to use up to a one to one or two to one ratio to ease application and or to decrease break time. Apply with a brush, broom, roller or spray equipment. Thin overlays should have an 8" wide band around the perimeter of the patch and apply at a rate of .06 to .10 gal/sq. yd. in the center areas. On excavated or utility patch repairs all vertical surfaces of existing pavement should be coated. *Do not apply when rain is imminent or when surface to be coated or surface and/or ambient air temperature is below 32°F (0°C).*

#### CURE TIME

Cure time will vary depending on weather conditions. Product will appear brown in color after applied. Apply patch material once tack coat has turned black.

#### STORAGE

DISSCO Tack Coat may be stored outdoors when ambient air temperatures are above 40°F (4°C). DISSCO Tack Coat is water base and will freeze. **KEEP FROM FREEZING.** Clean tools with water immediately after use.

#### CLEAN UP

Rinse tools with water immediately after use. If tack coat has dried, clean with mineral spirits or a good citrus-based degreaser.

**Denver Industrial Sales & Service Company**

850 South Lipan Street, Denver, CO 80223

Ph 303-935-2485 Fax 303-935-6787

[www.dissco.net](http://www.dissco.net)



PAVEMENT PRESERVATION SOLUTIONS

## DISSCO CSS1h PHYSICAL PROPERTIES

Color	Black
Weight per gallon	8.35-8.5 lbs.
Vehicle solids	60 – 70 %
Volatile vehicle	30 – 40 %
Boiling point	212°F Degrees (may be lower at higher altitudes)

## AVAILABILITY

DISSCO CSS1h is available in a concentrate form and is available in bulk and in packaged sizes of 5 gallon pails and 55 gallon drums.

## SPECIFICATION COMPLIANCE

DISSCO Tack Coat concentrate is manufactured to meet or exceed AASHTO M-208-96 and/or ASTM D-2397-98 specifications.

## CAUTION

Use with adequate ventilation. Vapor may be harmful. Avoid prolonged or repeated contact with skin or breathing of vapor. Close container tightly after each use. Harmful or fatal if swallowed. If swallowed, DO NOT INDUCE VOMITING. Call physician immediately. KEEP OUT OF REACH OF CHILDREN.

## WARRANTY

DISSCO warrants its products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on site conditions are beyond our control and can affect performance, DISSCO makes no other warranty, express or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to DISSCO coatings. DISSCO's sole obligation shall be, at its option, to replace, or to refund the purchase price of, the quality of DISSCO coating proved to be defective and DISSCO shall not be liable for any loss or damage, including incidental or consequential damages, arising from the use of DISSCO coatings.

For further information, please call (303) 935-2485.

**In case of an EMERGENCY involving any DISSCO product please call:  
Info-Trac @ 1-800-535-5053**

**Denver Industrial Sales & Service Company**

850 South Lipan Street, Denver, CO 80223

Ph 303-935-2485 Fax 303-935-6787

[www.dissco.net](http://www.dissco.net)